

Diamond 1020°-1100°



Rating: Not Rated Yet

Price

\$ 16.50

[Ask a question about this product](#)

Manufacturer [Walker Ceramics](#)

Description

NOT suitable for Food & Drink containers due to crackle. For Artistic use only. Cesco Powder Pooling Gloss Glaze. Firing Range 1020-1100°C. Earthenware

No Lead frit is used in the manufacture of this product.

Apply powdered glaze on horizontal surface or recess (up to 5mm) & glaze will form a glassy pool of colour when fired !!

Best results are on basic handbuilding clays to enhance the crackle effect!!