Midfire Clear Gloss BMG140 Northcote Brush On (1190-1220C)



Rating: Not Rated Yet **Price** \$ 26.70

Ask a question about this product

ManufacturerNorthcote Pottery

Description

Firing range: 1190-1220C

Manufacturer's instructions:

Shake well before use. Apply glaze using a soft brush. We recommend hake brushes. Apply 2-3 coats of glaze to ensure adequate thickness. 1-2 coats is sufficient for Clear Glazes. Allow glaze to dry in between coats. Fire glaze to recommended temperature.

Keep container lid clean and tightly sealed to avoid glaze dehydration. Keep container out of direct sunlight, temperatures above 30C or below 5C.