Sapphire 1020°-1100°



Rating: Not Rated Yet **Price** \$ 16.50

Ask a question about this product

ManufacturerWalker Ceramics

Description

NOT suitable for Food & Drink containers due to crackle. For Artistic use only. Cesco Powder Pooling Gloss Glaze. Firing Range 1020-1100°C. Earthenware

No Lead frit is used in the manufacture of this product.

Apply powdered glaze on horizontal surface or recess (up to 5mm) & glaze will form a glassy pool of colourwhen fired!! Best results are on basic handbuilding clays to enhance the crackle effect!!

1 / 1